

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 435 407 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
07.07.2004 Bulletin 2004/28

(21) Application number: **03000120.0**

(22) Date of filing: **02.01.2003**

(51) Int Cl.⁷: **D06M 13/292**, D06M 13/17,
D06M 15/53, D06M 15/356,
D06M 11/76, D06M 13/352,
B66B 7/12, B66D 1/54,
B66B 5/00, D07B 1/14

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT SE SI SK TR**
Designated Extension States:
AL LT LV MK RO

(71) Applicant: **Teijin Twaron B.V.**
6827 AV Arnhem (NL)

(72) Inventors:
• **Willemsen, Stephanus**
6991 TW Rheden (NL)

• **Stuut, Herman**
6824 AS Arnhem (NL)

(74) Representative: **Heimann, Anette et al**
CPW GmbH
Patentabteilung
Kasinostrasse 19-21
42103 Wuppertal (DE)

(54) **Aramid filament yarn provided with a conductive finish**

(57) The invention pertains to an aramid filament yarn provided with > 1.5 wt.% of a finish comprising an organic substance with a conductivity of > 4 mS/cm, measured as a 50 wt.% finish composition in water at

20°C, having a specific electric resistance of the yarn < 2.5.10⁴ Ohm.cm, and to a method of making said yarn.

EP 1 435 407 A1

Description

[0001] The invention pertains to an aramid filament yarn provided with a conductive finish, to a method of making such yarn, and to the use of said yarn.

[0002] A common problem of yarns is breaking of the yarn when used in certain applications. Yarn breaks may occur as a result of over-loading, fatigue, or wear. Ground cable damage may also occur as a result of damage caused by rodents. In elevator cables breakage of cables is a serious safety problem. It is known to add to aramid reinforced elevator cables, for example, one or more carbon yarns or metal wire as a break detector. Such treated aramid reinforced cables, however, do not have the same mechanical characteristics as cables made of untreated aramid yarns only. Moreover, the breaking characteristics of such carbon yarn or metal wire is different from the breaking characteristics of aramid yarn, thereby hampering accurate indication of breaking danger of the aramid reinforced cable. The other mechanical properties of non-aramid yarns in comparison to the main reinforcing material of the cable complicates the predictability of a cable breakage considerably. It would be an advantage to provide aramid yarn having sufficient conductive properties and nevertheless having the same mechanical characteristics as the untreated aramid yarns in the cable.

[0003] Some solutions to the above problems are proposed. In WO 9748832 the yarn was coated with a metal such as nickel with an acid. Such treatment provides metalized yarns, the fiber surfaces of which may be damaged by the acid treatment, leading to decrease of tenacity and/or elongation properties. In WO 9325748 a process was disclosed for treating aramid fibers with a dispersion of particulate graphite material in a swelling solvent. Also using this method bears the risk of damaging the fiber surface. Moreover, both methods are very complicated, time consuming, and therefore costly.

[0004] The present invention therefore provides in a solution of the above problems, using a simple procedure that is no time consuming, cheap, and without any risk of damaging the fibers. It was found that an aramid filament yarn provided with a finish comprising > 1.5 wt.% of an organic substance with a conductivity of > 4 mS/cm, measured as a 50 wt.% finish composition in water at 20°C, having a specific electric resistance of the yarn < 2.5.10⁴ Ohm.cm, possesses a sufficient conductivity to be used as a breaking detector, without affecting its mechanical properties. This is a substantial advantage over the use of, for example, a carbon yarn or a metal wire as break detector in aramid reinforced elevator cables. The conductivity of the organic substance treated and damaged yarn is reduced as a result of breaks caused by wear or fatigue and provides information to the user on the remaining lifetime of the cable. The conductivity of a yarn or a cable can be determined with a resistancy or multimeter.

When finishes comprising a conductive organic substance (COS) are applied onto aramid filament yarn, the electrical yarn resistance thereof is reduced. Depending on the amount of finish and on the conductivity of the applied organic substance, the treated yarn can be used as such, or in combination with untreated aramid filament yarn as an early break detector in (elevator, bearer, ground) cables, or for accessories (brushes, rollers) which have to lay on or to eliminate static electricity in, for example, record players, magnetic tapes, compact disks, and the like.

The conductive organic substance can be applied onto wet or dried yarn as a spin-finish (before or after the drying, as such or diluted with a solvent such as water) in the spinning process or in a separate process step at a relatively high yarn speed.

[0005] Aramid filament yarns treated with > 2 wt. % of a conductive organic substance with a conductivity of > 30 mS/cm are preferred. More preferred are yarns treated with > 2 % of a conductive organic substance with a conductivity of > 41 mS/cm. The specific electric resistance of the yarn is preferably < 2.10³ Ohm.cm, more preferably < 10³ Ohm.cm. particularly suitable amounts of COS are within the range 3 to 12 wt.%, more preferably within the range 4-9 wt.%. The wt.% is relative to the total weight of the yarn without finish.

[0006] Suitable organic substances that are suitable for use in the invention are salts or materials having statically chargeable acid or base groups. Materials with acid groups have preferably carboxylate, phosphonate or sulfonate groups. Materials with base groups have preferably amine groups.

Particularly preferred materials are fatty acids, carbonic acids, (cyclo)alkyl phosphates, (cyclo)alkyl phosphonates, (cyclo)alkyl sulfates, (cyclo)alkyl sulfonates, imidazoline derivatives and polymers such as poly(diallyldimethylammonium chloride), and the like.

[0007] The aramid yarns preferably are made of poly(p-phenylene terephthalamide) (PPDT), but may also contain minor amounts of other monomers.

[0008] The COS is applied onto the yarn by conventional methods known in the art. The COS can be applied in solution. The solvent may be any suitable solvent, such as alcohol, ether, tetrahydrofuran, acetone, benzene, toluene, ethyl acetate, dichloromethane and the like. Most preferably the COS is applied as an aqueous solution. Some COS's are purchased as a water-containing product that can be applied as such.

[0009] The suitable amount of COS to be applied can very easily be determined by a simple conductivity measurement, which as such is known in the art. When the conductivity of the COS or the solution of the COS is determined, a skilled person can easily apply the required amount of finish as needed for the specific use.

Procedure for the determination of the conductivity of a finish

[0010] A suitable procedure to determine the conductivity of a finish composition according to the invention is as follows.

A sufficient amount of the aqueous finish solution (50 wt.% of water and 50 wt.% of COS) to be tested is poured into a beaker. Subsequently, the conductivity of this solution is determined according DIN norm 38404 Teil 8 (9.1985) at a temperature of 20°C.

When the finish containing the COS has a lower or higher water content than 50 wt.%, the concentration of the finish solution should be adjusted to 50 wt.% by respectively the addition of demineralized water or the evaporation of water by heating on a hot plate under stirring at an elevated temperature below 100°C. For the measurement of the conductivity a conductivity meter type LF 537 of the Wissenschaftlich-Technische Werkstätten GmbH, Weilheim, Germany was used.

The water content of the finish solution was determined by the Karl Fischer method. An exact description of the determination of water via Karl Fischer reagent is given in "Karl Fischer Titration, Methoden zur Wasserbestimmung" by Eugen Scholz, Springer-Verlag 1984.

Procedure for the determination of the specific electrical resistance

[0011] For the determination of the specific electrical resistance of the aramid yarns a sample-holder consisting of two copper bars separated by two polytetrafluorethylene rods was used. The mutual distance of the bars is 52 mm. The yarn to be tested is wound a number of times (preferably between 3 and 7) times around the two copper bars which are connected with a DC high voltage power source and a Keithley electrometer. With the Keithley electrometer the electrical current was determined after a voltage of 500 V was applied over the copper bars at 20°C and 65% relative humidity. The specific electrical resistance of the yarn was calculated based on Ohm's law, the yarn length between the copper bars, the number of yarn connections, and the cross-section area of the yarn.

[0012] The invention is further illustrated with the following non-limitative examples.

Example 1

[0013] This example illustrates the procedure of applying a finish containing a conductive organic substance (COS) to a wet, not previously dried, yarn in an operation integrated with the spinning process. A spinning mass was prepared by mixing concentrated (99.8 wt.%) sulfuric acid snow with powdered poly-p-phenylene terephthalamide. The spinning mass was de-aerated, heated to 90°C in a double-screw extruder and fed to a spinneret via a filter and a spinning pump. The spinneret had 1000 orifices of 59 micrometer in diameter. The spinning mass was extruded through the spinning orifices and thereafter successively passed through an air zone of 8 mm in length and a coagulation bath. This bath was a dilute solution of sulfuric acid in water (about 19% by weight) having a temperature of 5°C. The filament bundle thus formed successively passed through a neutralization bath containing a dilute sodium carbonate solution and a washing bath in which the filaments were thoroughly washed with water of about 75°C. Excess adhering water was removed with the aid of a squeeze roller pair. Next, the non-dried bundle of filaments was provided with an aqueous finish containing a COS with the aid of a liquid applicator and a feed pump. Next the yarn was passed over a series of 3 drying drums (6 wraps of 160°C, 6 wraps of 180°C, 4 wraps of 200°C). The yarn was in contact with the surface of the drums for 5-6 seconds in all. Subsequently, the yarn was passed over a transport drum (4 wraps of about 20°C) and was wound into a package at a speed of 400 m/min. The yarn obtained had a linear density of 1610 dtex. The following process conditions were varied (table A and B):

- a) the composition of the finish containing the COS
- b) the amount of COS on yarn

Table A

| Aqueous finishes containing conductive organic substances | | | | |
|---|-------------------------|----------|----------|----------|
| Finish concentration in wt.% | Finish composition code | | | |
| | a1 20 | b1 20 | c1 20 | d1 20 |
| COS in solution (%) | | | | |

EP 1 435 407 A1

Table A (continued)

| Aqueous finishes containing conductive organic substances | | | | |
|---|-------------------------|----------|----------|----------|
| Finish concentration in wt. % | Finish composition code | | | |
| | a1 20 | b1 20 | c1 20 | d1 20 |
| Afilan V4855 (37.6%) | 53,2 | 37,2 | | |
| Afilan PTU | | 6,0 | | |
| PolyDADMAC (42.4%) | | | 47,1 | |
| Tallopol ACF (50.5%) | | | | 39,6 |
| Demineralized water | 46,8 | 56,8 | 52,9 | 60,4 |

Afilan V4855 is an alkane phosphonate, potassium salt, ex-Clariant GmbH, Frankfurt, Germany.
Afilan PTU is an ethoxylated and propoxylated oleic acid, CH₃-capped, ex-Clariant GmbH, Frankfurt, Germany.
PolyDADMAC is the abbreviation of poly(diallyldimethylammonium chloride) with a low mol weight; catalog nr. 52237-6, supplier Aldrich Chemical Company, Inc., Milwaukee, USA.
Tallopol ACF is a product mixture of potassium and sodium salts of carbonic acids, ex-Stockhausen, Krefeld, Germany.

Table B

| The specific electrical resistance | | | | | |
|--|---------|---------|---------|---------|---------|
| Experiment No. | 1A | 1B | 1C | 1D | 1E |
| Finish composition applied with applicator | a1 | b1 | b1 | c1 | d1 |
| COS amount on yarn (wt.%) | 3,0 | 3,0 | 4,0 | 4,0 | 4,0 |
| Conductivity of a 50 wt. % finish composition in mS/cm at 20°C | 42,6 | 43,7 | 43,7 | 45,4 | 215,0 |
| Specific electrical resistance of the yarn in Ohm.cm | 3,5E+03 | 6,5E+03 | 2,8E+03 | 2,8E+03 | 5,8E+02 |

Comparative Example 1

[0014] This comparative example relates to an experiment in which the yarn of Example 1 was provided with 0.9% of a non-ionic finish normally used for the spinning of Twaron® yarns. The conductivity of the finish solution (50 wt.%) was 0.009 mS/cm. The obtained yarn showed a specific electrical resistance of 7.2E+07 Ohm.cm.

Example 2

[0015] This example illustrates the procedure of applying a finish containing a conductive organic substance (COS) to a dried yarn in an operation integrated with the spinning process. The spinning mass of Example 1 was extruded through a spinneret which had 2000 orifices of 59 micrometer in diameter and was thereafter successively passed through the same air zone, coagulation, neutralization, and washing bath as described in Example 1. Excess adhering water was removed with the aid of a squeeze roller pair. Next, the yarn was passed over a series of 3 drying drums (6 wraps of 160°C, 6 wraps of 180°C, 4 wraps of 250°C). The yarn was in contact with the surface of the drums for about 7 seconds in all. Next, the completely dried bundle of filaments was provided with an aqueous finish containing a COS with the aid of a liquid applicator and a feed pump. Subsequently, the yarn was passed over a transport drum (4 wraps of about 20°C) and was wound into a package at a speed of 300 m/min. The yarn obtained had a linear density of 3220 dtex. The following process conditions were varied (table C and D):

- the composition of the finish containing the COS
- the amount of COS on yarn
- the concentration of the finish solution

Table C

| Aqueous finishes containing conductive organic substances | | | |
|---|-------------------------|------------|----------|
| Finish concentration in wt.% | Finish composition code | | |
| | a2 37,6 | b2 46,3 | d2 50 |
| COS in solution (%) | | | |
| Afilan V4855 (37.6%) | 100,0 | 86,1 | |
| Afilan PTU | | 13,9 | |
| Tallopol ACF (50.5%) | | | 99,0 |
| Demineralized water | | | 1,0 |

Table C

| The specific electrical resistance | | | |
|---|---------|---------|---------|
| Experiment No. | 2A | 2B | 2C |
| Finish composition applied with applicator | a2 | b2 | d2 |
| COS amount on yarn (wt.%) | 3,0 | 3,5 | 2,5 |
| Conductivity of a 50 wt.% finish composition in mS/cm at 20°C | 42,6 | 43,7 | 215,0 |
| Specific electrical resistance of the yarn in Ohm.cm | 7,8E+03 | 7,2E+03 | 9,6E+02 |

Example 3

[0016] This example illustrates the application of a finish containing a conductive organic substance (COS) to a dried yarn not directly coupled to the spinning process. Commercially available Twaron® 2200 (1610 dtex/f 1000) yarn was subjected to the following treatments. The yarn package was rollingly unwound while successively passing the yarn over a liquid applicator, through a steam box (temperature 240°C, residence time 8 seconds) and finally wound into a package at a speed of 75 m/min. With the liquid applicator and a feed pump, the yarn was coated with the finishes mentioned in table E and F. The following process conditions were varied:

- a) the composition of the finish containing the COS
- b) the amount of COS on yarn
- c) the concentration of the finish solution

Table E

| Aqueous finishes containing conductive organic substances | | | | |
|---|-------------------------|----------|----------|----------|
| Finish concentration in wt.% | Finish composition code | | | |
| | a3 15 | d3 10 | d4 15 | d1 20 |
| COS in solution (%) | | | | |
| Afilan V4855 (37.6%) | 40,0 | | | |
| Tallopil ACF (50.5%) | | 19,8 | 29,7 | 39,6 |
| Demineralized water | 60,0 | 80,2 | 70,3 | 60,4 |

Table F

| The specific electrical resistance | | | | |
|---|---------|---------|---------|---------|
| Experiment No. | 3A | 3B | 3C | 3D |
| Finish composition applied with applicator | a3 | d3 | d4 | d1 |
| COS amount on yarn (wt.%) | 2,5 | 2,0 | 3,0 | 4,0 |
| Conductivity of a 50 wt.% finish composition in mS/cm at 20°C | 42,6 | 215,0 | 215,0 | 215,0 |
| Specific electrical resistance of the yarn in Ohm.cm | 3,9E+03 | 2,9E+03 | 1,8E+03 | 8,8E+02 |

Example 4

[0017] This example illustrates the application of a finish containing a conductive organic substance (COS) to a dried yarn not directly coupled to the spinning process. Commercially available Twaron® 2200 (3220 dtex/f 2000) yarn was subjected to the following treatments. The yarn package was unwound while successively passing the yarn over a double rotating kiss-roll and through a hot air oven (temperature 180°C, residence time 18 seconds) and was finally wound into a package at a speed of 100 m/min. With the double kiss-roll the yarn was coated with the finishes mentioned in table G and H. The following process conditions were varied:

- a) the composition of the finish containing the COS
- b) the amount of COS on yarn
- c) the concentration of the finish solution

Table G

| Aqueous finishes containing conductive organic substances | | |
|---|-------------------------|----------|
| Finish concentration in wt.% | Finish composition code | |
| | a1 20 | d4 15 |
| COS in solution (%) | | |
| Afilan V4855 (37.6%) | 53,2 | |
| Tallopul ACF (50.5%) | | 29,7 |
| Demineralized water | 46,8 | 70,3 |

Table H

| The specific electrical resistance | | |
|---|---------|---------|
| Experiment No. | 4A | 4B |
| Finish composition applied with applicator | a1 | d4 |
| COS amount on yarn (wt.%) | 10,3 | 5,6 |
| Conductivity of a 50 wt.% finish composition in mS/cm at 20°C | 42,6 | 215,0 |
| Specific electrical resistance of the yarn in Ohm.cm | 3,5E+03 | 1,2E+03 |

Example 5

[0018] This example illustrates the application of a finish containing a conductive organic substance (COS) to a dried

and finish-free yarn not directly coupled to the spinning process. A package of finish-free Twaron® (1610 dtex/f 1000) yarn was subjected to the following treatments. The yarn package was unwound while successively passing the yarn over a liquid applicator, through a hot air oven (temperature 90°C, residence time 32 seconds) and was finally wound into a package at a speed of 50 m/min. With the liquid applicator and a feed pump, the yarn was coated with the finishes mentioned in table K and L. The following process conditions were varied:

- a) the composition of the finish containing the COS
- b) the amount of COS on yarn
- c) the concentration of the finish solution

Table K

| Aqueous finishes containing conductive organic substances | | | |
|---|-------------------------|----------|----------|
| Finish concentration in wt.% | Finish composition code | | |
| | e1 20 | f1 32 | g1 20 |
| COS in solution (%) | | | |
| Leomin AN | 20,0 | 16,0 | |
| Leomin OR | | 16,0 | |
| Atlas G3634a | | | 20,0 |
| Demineralized water | 80,0 | 68,0 | 80,0 |
| Leomin AN is an ethyl octane phosphonate, potassium salt; ex Clariant GmbH, Frankfurt, Germany. Leomin OR is a polyglycol ester of a fatty acid, ex Clariant GmbH, Frankfurt, Germany. Atlas G3634a is an imidazoline derivate, quarternized, ex Uniqema, Middlesbrough, England. | | | |

Table L

| The specific electrical resistance | | | |
|---|---------|---------|---------|
| Experiment No. | 5A | 5B | 5C |
| Finish composition applied with applicator | e1 | f1 | g1 |
| COS amount on yarn (wt.%) | 5,0 | 8,0 | 5,0 |
| Conductivity of a 50 wt.% finish composition in mS/cm at 20°C | 40,8 | 15,2 | 4,7 |
| Specific electrical resistance of the yarn in Ohm.cm | 2,2E+03 | 5,6E+03 | 2,2E+04 |

Claims

1. An aramid filament yarn provided with a finish comprising > 1.5 wt.% of an organic substance with a conductivity of > 4 mS/cm, measured as a 50 wt.% finish composition in water at 20°C, having a specific electric resistance of the yarn < 2.5.10⁴ Ohm.cm.
2. The aramid filament yarn of claim 1 provided with a finish comprising > 2 wt.% of an organic substance with a conductivity of > 30 mS/cm, measured as a 50 wt.% finish composition in water at 20°C, having a specific electric resistance of the yarn < 2.10³ Ohm.cm.
3. The aramid filament yarn of claim 1 or 2 provided with a finish comprising > 2 wt.% of an organic substance with a conductivity of > 41 mS/cm, measured as a 50 wt.% finish composition in water at 20°C, having a specific electric resistance of the yarn < 10³ Ohm.cm.

EP 1 435 407 A1

4. A method of making the yarn of claim 1 having a specific electric resistance of the yarn $< 2.5 \cdot 10^4$ Ohm.cm, comprising bringing a solution of an organic substance onto the aramid yarn such as to obtain > 1.5 wt.% of the substance relative to the total weight of the yarn without the finish, **characterized in that** the organic substance has a conductivity of > 4 mS/cm, measured as a 50 wt.% finish composition in water at 20°C.

5. Use of the yarn of claim 1 in conductive aramid-containing materials.

6. Use of the yarn of claim 1 in lift cables.

7. Use of the yarn of claim 1 in fibers for transporting electric current or for eliminating static electricity.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 00 0120

| DOCUMENTS CONSIDERED TO BE RELEVANT | | | |
|--|---|---|--|
| Category | Citation of document with indication, where appropriate, of relevant passages | Relevant to claim | CLASSIFICATION OF THE APPLICATION (Int.Cl.7) |
| X | US 5 478 648 A (STEIN GERHARD ET AL) 26 December 1995 (1995-12-26) | 1-5,7 | D06M13/292 |
| Y | * column 1, line 43 - column 2, line 64 * | 6 | D06M13/17 |
| | --- | | D06M15/53 |
| Y | US 5 834 942 A (DE ANGELIS CLAUDIO) 10 November 1998 (1998-11-10) | 6 | D06M15/356 |
| | * column 1, line 52 - line 62 * | | D06M11/76 |
| | * column 2, line 15 - line 62 * | | D06M13/352 |
| | --- | | B66B7/12 |
| X | US 5 674 615 A (NEUERT RICHARD ET AL) 7 October 1997 (1997-10-07) | 1-5,7 | B66D1/54 |
| | * column 1, line 43 - column 2, line 14 * | | B66B5/00 |
| | * column 6, line 35 - line 41 * | | D07B1/14 |
| | --- | | |
| X | EP 0 416 486 A (DU PONT) 13 March 1991 (1991-03-13) | 1,4,5,7 | |
| | * page 4, line 24 - page 5, line 42 * | | |
| | --- | | |
| X | WO 92 15747 A (DU PONT) 17 September 1992 (1992-09-17) | 1,4,5,7 | |
| | * page 2, line 11 - page 3, line 32 * | | |
| | * page 8, line 4 - line 7 * | | |
| | --- | | |
| A | EP 0 423 703 A (DU PONT) 24 April 1991 (1991-04-24) | 1-7 | |
| | * page 2, line 33 - line 40 * | | |
| | ----- | | |
| The present search report has been drawn up for all claims | | | |
| Place of search THE HAGUE | | Date of completion of the search 21 August 2003 | Examiner Fiocco, M |
| CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document | | | |

EPO FORM 1503 (3.82 (P04C01))

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 00 0120

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

21-08-2003

| Patent document cited in search report | | Publication date | | Patent family member(s) | Publication date |
|---|---|---------------------|----|----------------------------|---------------------|
| US 5478648 | A | 26-12-1995 | DE | 4402193 C1 | 01-06-1995 |
| | | | EP | 0665323 A2 | 02-08-1995 |
| | | | JP | 7229059 A | 29-08-1995 |
| ----- | | | | | |
| US 5834942 | A | 10-11-1998 | AT | 181977 T | 15-07-1999 |
| | | | AU | 700649 B2 | 14-01-1999 |
| | | | AU | 4584896 A | 19-09-1996 |
| | | | BR | 9600892 A | 30-12-1997 |
| | | | CA | 2169431 A1 | 07-09-1996 |
| | | | CN | 1134484 A ,B | 30-10-1996 |
| | | | CZ | 9600649 A3 | 11-09-1996 |
| | | | DE | 59602355 D1 | 12-08-1999 |
| | | | DK | 731209 T3 | 17-01-2000 |
| | | | EP | 0731209 A1 | 11-09-1996 |
| | | | ES | 2136335 T3 | 16-11-1999 |
| | | | HK | 1011391 A1 | 28-04-2000 |
| | | | HU | 9600548 A2 | 28-05-1997 |
| | | | JP | 8261972 A | 11-10-1996 |
| | | | NO | 960880 A | 09-09-1996 |
| | | | NZ | 286035 A | 24-06-1997 |
| | | | PL | 313088 A1 | 16-09-1996 |
| | | | RU | 2148117 C1 | 27-04-2000 |
| | | | TR | 960867 A2 | 21-10-1996 |
| | | | ZA | 9601733 A | 10-09-1996 |
| ----- | | | | | |
| US 5674615 | A | 07-10-1997 | DE | 4410708 C1 | 13-07-1995 |
| | | | EP | 0675222 A2 | 04-10-1995 |
| ----- | | | | | |
| EP 0416486 | A | 13-03-1991 | DE | 3929376 C1 | 18-04-1991 |
| | | | AU | 619695 B2 | 30-01-1992 |
| | | | AU | 6214790 A | 14-03-1991 |
| | | | BR | 9004398 A | 10-09-1991 |
| | | | CA | 2024268 A1 | 06-03-1991 |
| | | | CN | 1050573 A | 10-04-1991 |
| | | | DE | 69007909 D1 | 11-05-1994 |
| | | | DE | 69007909 T2 | 25-08-1994 |
| | | | EP | 0416486 A2 | 13-03-1991 |
| | | | ES | 2063220 T3 | 01-01-1995 |
| | | | IE | 903202 A1 | 13-03-1991 |
| | | | JP | 2893652 B2 | 24-05-1999 |
| | | | JP | 3104929 A | 01-05-1991 |
| | | | KR | 138982 B1 | 15-05-1998 |
| | | | NO | 903857 A | 06-03-1991 |
| | | | TR | 24686 A | 01-03-1992 |
| | | | US | 5139873 A | 18-08-1992 |
| | | | US | 5270113 A | 14-12-1993 |

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 00 0120

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

21-08-2003

| Patent document cited in search report | Publication date | Patent family member(s) | Publication date |
|---|---------------------|----------------------------|----------------------------|
| EP 0416486 | A | ZA 9007071 A | 27-05-1992 |
| ----- | ----- | ----- | ----- |
| WO 9215747 | A | 17-09-1992 | CN 1076977 A ,B 06-10-1993 |
| | | DE 4106682 A1 | 08-10-1992 |
| | | AU 660455 B2 | 29-06-1995 |
| | | AU 1460892 A | 06-10-1992 |
| | | BR 9205704 A | 02-08-1994 |
| | | DE 69200321 D1 | 15-09-1994 |
| | | DE 69200321 T2 | 09-02-1995 |
| | | EP 0574507 A1 | 22-12-1993 |
| | | ES 2057991 T3 | 16-10-1994 |
| | | JP 3383860 B2 | 10-03-2003 |
| | | JP 6505312 T | 16-06-1994 |
| | | WO 9215747 A1 | 17-09-1992 |
| | | US 5270113 A | 14-12-1993 |
| | | CA 2105092 A1 | 03-09-1992 |
| | | KR 215686 B1 | 16-08-1999 |
| ----- | ----- | ----- | ----- |
| EP 0423703 | A | 24-04-1991 | AU 629993 B2 15-10-1992 |
| | | AU 6465690 A | 18-04-1991 |
| | | BR 9005205 A | 17-09-1991 |
| | | CA 2027661 A1 | 17-04-1991 |
| | | CN 1051770 A | 29-05-1991 |
| | | EP 0423703 A2 | 24-04-1991 |
| | | IE 903679 A1 | 24-04-1991 |
| | | JP 3185180 A | 13-08-1991 |
| | | NO 904449 A | 17-04-1991 |
| | | PT 95604 A | 30-09-1991 |
| ----- | ----- | ----- | ----- |